

## CLAIMS

What is claimed is:

- 5           1.    An organic electronic device, comprising:  
            a deposition surface;  
            a photo-resist layer, said photo-resist layer fabricated  
            upon said deposition surface, said photo-resist layer patterned  
            into a plurality of banks to define pockets upon said deposition  
10     surface; and  
            an organic layer, said organic layer composed of a dried  
            film resulting from drying a reformulated organic solution upon  
            said deposition surface and within said pockets, said  
            reformulated organic solution comprised of a mixture of base  
15     organic solution and humectants, further wherein the surface  
            energy of said deposition surface is much lower than the surface  
            energy of said photo-resist layer banks, said dried film having  
            a substantially flat and uniform profile.
- 20           2.    A device according to claim 1 wherein said organic  
            layer is a conducting polymer layer.

3. A device according to claim 2 wherein said reformulated organic solution includes a base conducting polymer solution, humectants and water.

5 4. A device according to claim 1 wherein said device is treated with a plasma process to selectively cause said deposition surface to be more hydrophilic and said photo-resist banks to be more hydrophobic.

10 5. A device according to claim 2 wherein said organic electronic device is a OLED device.

6. A device according to claim 5 wherein said deposition surface is the lower electrode layer.

15 7. A device according to claim 6 further comprising an emissive layer, said emissive layer fabricated over said conducting polymer layer, said emissive layer emitting light upon charge recombination.

20 8. A device according to claim 7 further comprising a cathode layer disposed over said emissive layer.

9. A device according to claim 3 wherein said base  
conducting polymer solution is a PEDOT:PSS solution.

10. A device according to claim 9 wherein the ratio of  
5 PEDOT to PSS is one part to six parts, respectively.

11. A device according to claim 10 wherein the ratio of  
base conducting polymer solution to humectants to water is  
thirty parts to forty parts to thirty parts, respectively.

10

12. A device according to claim 1 wherein said device is  
an organic transistor.

13. A device according to claim 1 wherein said device is  
15 an organic solar cell.

14. A method of fabricating an organic electronic device,  
said method comprising:

patterning a lower electrode layer upon a substrate, said  
20 lower electrode layer having a top exposed deposition surface;

fabricating a photo-resist layer upon said lower electrode  
layer, said photo-resist layer patterned to define pockets on  
said deposition surface;

treating said device to raise the surface energy of said deposition surface and lower the surface energy of said photo-resist layer;

reformulating an organic solution by mixing a base organic  
5 solution with humectants; and

depositing drops of said reformulated solution into each said pocket, said drops allowed to dry into an organic layer, said organic layer having a substantially flat and uniform profile.

10

15. A method according to claim 14 wherein said treating includes applying a fluorinating plasma process.

16. A method according to claim 14 wherein said organic  
15 electronic device is an organic light emitting diode (OLED) display.

17. A method according to claim 16 wherein said lower electrode layer functions as an anode.

20

18. A method according to claim 17 wherein said organic layer is a conducting polymer layer.

19. A method according to claim 18 further comprising:

fabricating an emissive layer above said conducting polymer layer, said emissive layer emitting light upon charge recombination.

5           20. A method according to claim 18 wherein said base organic solution is a PEDOT:PSS solution.

21. A method according to claim 20 wherein the ratio of PEDOT to PSS is one part to six parts, respectively.

10

22. A method according to claim 21 wherein the ratio of base organic solution to humectants to water is thirty parts to forty parts to thirty parts, respectively.

15           23. A method according to claim 14 wherein said device is an organic transistor.

24. A method according to claim 14 wherein said device is an organic solar cell.

20

25. A method according to claim 15 wherein said fluorinating plasmas process uses sulfur hexafluoride.

26. A method according to claim 14 wherein said humectants are at least one of glycols and glycol derivatives.